



Polyminerals Trading DMCC

JLT, Cluster Y, Swiss Tower, Floor 36, Office 3604, Dubai – UAE

Tel.: +971 04 558 7931

Mob: +971 52 747 2955

pulp@polyminerals.ae

Bleached Hardwood and Softwood Kraft pulp

Brightness, % min		88.0
Mechanical strength, while milling up to 60-degree SR	Breaking length, m	10.5
	Bursting strength, kPa	549
	Double Folding	1300
	Tensile index, Nm/g	103
	Burst index, kPa m ² /g	7.2
	Tear index, mN m ² /g	9.9
pH		6.7
Dirt content, pieces, for dust particles with an area:		
from 0.1 to 1.0 mm ²		3
from 1.0 to 2.0 mm ²		0
from 2.0 to 3.0 mm ²		0
above 3.0 mm ²		0
Mass 1m ² , g		1161
Compound composition, %	Hardwood	70
	Softwood	30
Humidity, %	min	6
	max	8.2
Mass fraction of Ash, % not more		0.37