



Polyminerals Trading DMCC

JLT, Cluster Y, Swiss Tower, Floor 36, Office 3604, Dubai – UAE

Tel.: + 971 04 558 7931

Mob: +971 52 747 2955

pulp@polyminerals.ae

Bleached Softwood Kraft pulp

Brightness, % min		88.4
Mechanical strength, while milling up to 60 degree SR	Breaking length, m	9.3
	Bursting strength, kPa	505
	Double Folding	1400
	Tensile index, Nm/g	91
	Burst index, kPa m ² /g	6.7
pH		7.0
Dirt content, pieces, for dust particles with an area:		
from 0.1 to 1.0 mm ²		1
from 1.0 to 2.0 mm ²		0
from 2.0 to 3.0 mm ²		0
above 3.0 mm ²		0
Mass 1m ² , g		1079